

Alfresco Range Technical Data Sheet

BRICKWORKS

Product Range	Name	Swatch Image	State	Length	Width	Height	Dimensional Category	Units per sqm	Pack Size	Characteristic Unconfined Compressive Strength	Durability Class	Slip Resistance	Liability To Effloresce	Lime Pitting Liability	Solar Absorption	Lrv
Alfresco	Buttermilk		NSW	230	115	50	DPA2	37	480	>10	Exposure Grade	P5	Slight	Slight		25
Alfresco	Roux		NSW	230	115	50	DPA2	37	480	>10	Exposure Grade	P5	Slight	Slight		9.6
Alfresco	Hickory		NSW	230	115	50	DPA2	37	480	>10	Exposure Grade	P5	Slight	Slight	0.78	8.2

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.



Please note: FRL applies up to 3m high - restrained on top and bottom.