



La Paloma Special Shapes Range Technical Data Sheet

BRICKWORKS

Product Range	Name	Dimension Illustration	Swatch Image	State	Length	Width	Height	Dimensional Category	Units per sqm	Pack Size	Characteristic Unconfined Compressive Strength	Compressive Strength	Initial Rate Of Absorption	Durability Class	Liability To Effloresce	Lime Pitting Liability	Solar Absorption	Lrv	Basix
La Paloma Special Shapes	Miro			NSW	236	114	65	DW1	48.5	432	>15		0.1-0.8	Exposure Grade	Slight	Slight	0.2	65.7	Light
La Paloma Special Shapes	Azul			NSW	230	110	76	DW1	54.5	448	>15		0.1-0.8	Exposure Grade	Slight	Slight	0.86	13.3	Dark
La Paloma Special Shapes	Miro			NSW	230	110	76	DW1	48.5	432	>15		0.1-0.8	Exposure Grade	Slight	Slight	0.2	65.7	Light
La Paloma Special Shapes	Azul			NSW	236	114	65	DW1	54.5		>15	>20	0.1-0.8	Exposure Grade	Slight	Slight	0.86	13.3	Dark
La Paloma Special Shapes	Azul			NSW	230	110	76	DW1	48.5	432	>15		0.1-0.8	Exposure Grade	Slight	Slight	0.86	13.3	Dark
La Paloma Special Shapes	Miro			NSW	230	110	76	DW1	54.5	448	>15		0.1-0.8	Exposure Grade	Slight	Slight	0.2	65.7	Light

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.



Please note: FRL applies up to 3m high - restrained on top and bottom.