

London Range Technical Data Sheet

BRICKWORKS

Product Range	Name	Dimension Illustration	Swatch Image	State	Length	Width	Height	Dimensional Category	Core Volume (%)	Units per sqm	Pack Size	Characteristic Unconfined Compressive Strength	Initial Rate Of Absorption	Durability Class	Slip Resistance	Liability To Effloresce	Lime Pitting Liability	Solar Absorption	Lrv	Basix	Frl
London	Silver Sand			NSW	230	114	65	DPA1	Solid	38	384	NA	1 to 8	Exposure Grade	P5	Slight	Slight				180/180/90
London	Chestnut			NSW	230	114	65	DPA1	Solid	38	384	NA	1 to 8	Exposure Grade	P5	Slight	Slight				180/180/90
London	Bowral Blue			NSW	230	114	65	DPA2	Solid	38	384	NA	1 to 8	Exposure Grade	P5	Slight	Slight	0.838	7.78	Dark	180/180/90
London	Regency Grey			NSW	230	114	65	DPA1	Solid	38	384	NA	1 to 8	Exposure Grade	P5	Slight	Slight				180/180/90
London	Brahman Granite			NSW	230	114	65	DPA2	Solid	38	384	NA	1 to 8	Exposure Grade	P5	Slight	Slight	0.7915	10	Dark	180/180/90
London	Maple			NSW	230	114	65	DPA1	Solid	38	384	NA	1 to 8	Exposure Grade	P5	Slight	Slight				180/180/90

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.

Please note: FRL applies up to 3m high - restrained on top and bottom.

BOWRAL BRICKS