

Thin Brick Range Technical Data Sheet

BRICKWORKS

Product Range	Name	Dimension Illustration	Swatch Image	State	Length	Width	Height	Dimensional Category	Units per sqm	Pack Size	Initial Rate Of Absorption	Durability Class	Liability To Effloresce	Lime Pitting Liability	Lrv	Basix
Thin Brick	Limewash Corner Unit			NSW	230	110	76	DW0		1008	4.0-8.0	General Purpose	Slight	Slight		Medium
Thin Brick	Original Facing Unit			NSW	230	22	76	DW0	48.5	2160	4.0-8.0	General Purpose	Slight	Slight		Light
Thin Brick	Castellana Corner Unit			NSW	230	110	76	DW1		1200		Exposure Grade	Slight		67	Light
Thin Brick	Limewash Facing Unit			NSW	230	22	76	DW0	48.5	2160	4.0-8.0	General Purpose	Slight	Slight		Medium
Thin Brick	Azul Facing Unit			NSW	230	22	76	DW1	48.5	1920		Exposure Grade	Slight		13.1	Dark
Thin Brick	Glazed White Corner Unit			NSW	230	110	76	DW1		1200		Exposure Grade	Slight		66.4	Light
Thin Brick	Wild Storm Facing Unit			NSW	230	22	76	DW0	48.5	2160	4.0-8.0	General Purpose	Slight	Slight	14.1	Dark
Thin Brick	Aged Red Corner Unit			NSW	230	110	76	DW0		1008	4.0-8.0	General Purpose	Slight	Slight		Medium
Thin Brick	Cloudy Silver Corner Unit			NSW	230	110	76	DW0		1008	4.0-8.0	General Purpose	Slight	Slight	22.8	Medium
Thin Brick	Castellana Facing Unit			NSW	230	22	76	DW1	48.5	1920		Exposure Grade	Slight		67	Light
Thin Brick	Glazed White Facing Unit			NSW	230	22	76	DW1	48.5	1920		Exposure Grade	Slight		66.4	Light
Thin Brick	Glazed Black Facing Unit			NSW	230	22	76	DW1	48.5	1920		Exposure Grade	Slight		1	Dark
Thin Brick	Miro Facing Unit			NSW	230	22	76	DW1	48.5	1920		Exposure Grade	Slight		63.7	Light
Thin Brick	Cloudy Silver Facing Unit			NSW	230	22	76	DW0	48.5	2160	4.0-8.0	General Purpose	Slight	Slight	22.8	Medium
Thin Brick	Miro Corner Unit			NSW	230	110	76	DW1		1200		Exposure Grade	Slight		63.7	Light
Thin Brick	Grey Cashmere Corner Unit			NSW	230	110	76	DW0		1008	4.0-8.0	General Purpose	Slight	Slight	45.5	Medium
Thin Brick	Azul Corner Unit			NSW	230	110	76	DW1		1200		Exposure Grade	Slight		13.1	Dark

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.



Please note: FRL applies up to 3m high - restrained on top and bottom.

Product Range	Name	Dimension Illustration	Swatch Image	State	Length	Width	Height	Dimensional Category	Units per sqm	Pack Size	Initial Rate Of Absorption	Durability Class	Liability To Effloresce	Lime Pitting Liability	Lrv	Basix
Thin Brick	Original Corner Unit			NSW	230	110	76	DW0		1008	4.0-8.0	General Purpose	Slight	Slight		Light
Thin Brick	Grey Cashmere Facing Unit			NSW	230	22	76	DW0	48.5	2160	4.0-8.0	General Purpose	Slight	Slight	45.5	Medium
Thin Brick	Wild Storm Corner Unit			NSW	230	110	76	DW0		1008	4.0-8.0	General Purpose	Slight	Slight	14.1	Dark
Thin Brick	Opaque Slate Facing Unit			NSW	230	22	76	DW0	48.5	2160	4.0-8.0	General Purpose	Slight	Slight	24.9	Medium
Thin Brick	Romero Corner Unit			NSW	230	110	76	DW1		1200		Exposure Grade	Slight		12	Dark
Thin Brick	Romero Facing Unit			NSW	230	22	76	DW1	48.5	1920		Exposure Grade	Slight		12	Dark
Thin Brick	Glazed Black Corner Unit			NSW	230	110	76	DW1		1200		Exposure Grade	Slight		1	Dark
Thin Brick	Opaque Slate Corner Unit			NSW	230	110	76	DW0		1008	4.0-8.0	General Purpose	Slight	Slight	24.9	Medium
Thin Brick	Aged Red Facing Unit			NSW	230	22	76	DW0	48.5	2160	4.0-8.0	General Purpose	Slight	Slight		Medium

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NZS 4456 ARE USED AS APPLICABLE.



Please note: FRL applies up to 3m high - restrained on top and bottom.